

fermacell AESTUVER Product Data Sheet



fermacell AESTUVER Repair Mortar Dry Motar

Product

AESTUVER Repair Mortar is a dry cement based mortar, with glass fibre reinforcement and lightweight additives. The AESTUVER Repair Mortar is used to repair areas of damage on AESTUVER boards.

Application

The base must be dust free and absorbent substrates should be pre-wetted. Do not use at temperatures below +5 °C. After curing (acclimatisation: 1–2 days), protect from weather and frost.

Mixing volume: 2 parts mortar to 1 part water.

Add the water to a clean mixing tub and then add the mortar and mix to a smooth, lump free consistency. Clean tools in clean water.

Properties

- Easy-to-handle
- Frost and weather-resistant
- Specially designed for use with AESTUVER boards

fermacell AESTUVER Repair Mortar

Material properties	
Packaging	Bucket – 8,5 kg
Workability	Ca. 60 minutes, depending on temperature.
Ambient Working temperature	Do not use at temperatures below +5 °C.
Solvent	Water
Mortar colour	grey
Storage	12 months; in dry storage

Merchant data	
Item number	9703075
EAN	40 0 7548 010924
Packaging	Bucket
Weight / Bucket	8,5 kg
Buckets / Pallet	45 pcs
Weight / pallet	413 kg

Further information

Mortar has an alkaline reaction with humidity, therefore, protect eyes and skin. In case of contact with skin rinse thoroughly with water. In case of eye contact consult doctor immediately.
Please refer to the label or the safety data sheet for further handling information pursuant to 1907/2006/EC, Article 31. Emergency number +49 - 551-19240

Our recommendations are based on extensive testing and practical experiences. They do not replace guidelines, standards, approvals and applicable technical data sheets. Due to the large number of possible influences for processing and application, we recommend that you carry out trial areas for processing and application. No claims for compensation may be derived from the information provided. Delivery, processing and the warranty on features assured by us will be in accordance with our GTCs.